Art Unit: 1615

CLMPTO 07/15/04 CB 12/02/04

CLAIMS 1-7 (ORIGINAL)

1. A process for making Compound (I), where Compound (I) comprises Compound (A),

(A)

and a polymer, wherein the polymer comprises lactide units, glycolide units and tartaric acid units where the ratio in the polymer of the lactide units is from and including 71% to 73%; of the glycolide units is from and including 26% to 28%; and of the tartaric acid units is from and including 1% to 3%; and where the amino group of Compound (A) is ionically bonded to a carboxylic group of the acid units of the polymer;

said process comprising the step of reacting an aqueous solution of Compound (A) with the polymer or a salt thereof, in a mixture of acetonitrile and water wherein the weight ratio of acetonitrile to water is about 3 to 1, respectively, at a temperature of about 0°C to 5°C until the formation of Compound (I) is substantially complete.

Art Unit: 1615

- 2. A process according to claim I wherein, the temperature is about 2.5°C; and said process comprises the additional step of isolating Compound (I).
- 3. A process for making microparticles of Compound (I), where Compound (I) comprises Compound (A),

$$\mathsf{HO}(\mathsf{CH}_2)_2\text{-}\mathsf{N}\text{-}(\mathsf{CH}_2)\text{-}\mathsf{CO}\text{-}\mathsf{D}\text{-}\mathsf{Phe-c[Cys-Tyr-D-Trp-Lys-Abu-Cys]-Thr-}\mathsf{NH}_2$$

(A)

and a polymer, wherein the polymer comprises lactide units, glycolide units and tartaric acid units where the ratio in the polymer of the lactide units is from and including 71% to 73%; of the glycolide units is from and including 26% to 28%; and of the tartaric acid units is from and including 1% to 3%; and where the amino group of Compound (A) is ionically bonded to a carboxylic group of the acid units of the polymer;

said process comprising the steps of:

nebulizing an ethyl acetate solution of Compound (I) into isopropyl alcohol to obtain a dispersion of microparticles of Compound (I),

Art Unit: 1615

wherein the concentration of Compound (I) in the ethyl acetate solution is about 8% to about 12% (W/W); the rate of spraying the solution of Compound (I) from the nebulizer into the isopropyl alcohol is about 4.9 ml/minute to about 5.1 ml/minute; the frequency setting of the nebulizer is such that the nebulizer does not spit the ethyl acetate solution of Compound (I); the volume of isopropyl alcohol is about 20 to 30 times volumetric excess compared to the ethyl acetate volume; and the temperature of isopropyl alcohol is about -60°C to about -78°C;

allowing the isopropyl alcohol to warm to about 0°C to 22°C; and isolating said microparticles from the isopropyl alcohol.

- 4. A process according to claim 3, wherein the rate of spraying is about 5 ml/minute and the volume of isopropyl alcohol is about 20 times volumetric excess compared to the volume of ethyl acetate.
- 5. A process according to claim 4, wherein the polymer comprises about 72% lactide units, about 27% glycolide units and about 1% tartaric acid units.
- 6. A process according to claim 5, wherein the microparticles have a mean size of about 10 microns to about 100 microns.

Art Unit: 1615

7. A process according to claim 6, wherein the microparticles have a mean size of about 40 microns to about 70 microns.

CLAIMS 8-9 (CANCELED)